SINCE 1934

TECHNOBIT

TECHNOLOGY OF INSULATING MATERIALS

ANUBIWRAP

TAPE

HIGH QUALITY SELF ADHESIVE
ANTI- CORROSION
TAPE



THE WISE CHOICE

+20 222 394 167

sales@technogroup-egypt.com
admin@technogroup-egypt.com

+2 010 2771 4174

FACTORY
Zero/ 157 A , Kilo17 - Misr / Bilbis road
El-Mohandsen El-Arab Association,
Al Sharqia, Egypt.

HEAD OFFICE
60-Mahmasha Street Al-Shrabya,
Cairo - Egypt.

MADE IN EGYPT

WWW.TECHNOGROUP-EGYPT.COM

Description

ANUBIWRAP TAPE is a cold-applied anti-corrosion wrap based on a 1.65 mm thick bituminous rubber compound. The compound is laminated onto a tough, extruded PVC carrier, offering excellent conformability and controlled elasticity.
ANUBIWRAP TAPE is designed for below-grade protection of metal substrates against corrosion and electrolysis. It provides self-sealing overlaps and is highly resistant to cathodic elasticity.

Major Features

- Anti-corrosion Barrier
- Self-sealed Joints And Overlaps
- Cold-applied System
- Tough Yet Flexible Pvc Backing
- High Elongation Capacity
- Resistance To Cathodic Disbondment
- Strong Adhesion To Primed Steel And Self-overlaps
- Low Water Absorption And Vapor Permeability
- Excellent Dielectric Strength

Uses

- Corrosion Protection For Buried Pipelines
- Suitable For Medium To Large Diameter Pipes
- Designed For Heavy Or Ungraded Backfills
- Protection Of Joints And Rehabilitation Of Old Coatings
- Compatible With Steel, Ductile Iron, And Plastic Pipes

Width	Thickness	Length
1 M	1.65 mm	15, 20 UP TO 60 M

Storage & Handling

ANUBIWRAP TAPE should be kept in an upright position in a flat, properly ventilated and sheltered storage area away from sunrays.

ANUBIWRAP TAPE

HIGH QUALITY SELF ADHESIVE ANTI CORROSION TAPE

Test	Unit	Test Method	Typical Values
Backing Colour			**Black**
Total Thickness	mm	ASTM D1000	**1.65**
Backing Thickness	mm	ASTM D1000	**0.75**
Adhesive Thickness	mm	ASTM D1000	**0.75**
Cathodic Disbondment, 30 days	mm radial	ASTM G8	**<10**
Adhesion to Self*	N/mm	ASTM D1000	**2**
Adhesion to Primed Steel*	N/mm	ASTM D1000	**2**
Tensile Strength	N/mm^2	ASTM D638	**14**
Tensile Modulus	N/mm^2	ASTM D638	**37**
Tear Resistance	N	ASTM D1004	**50**
Elongation	%	ASTM D638	**270**
Dielectric Strength	kV	BS2782	**30**
Holiday Detection Setting	kV	NACE RP0274	**10**
Impact Resistance	J	ASTM G13	**10**
Water Vapor Permeability	$g/(24h*m^2)$	ASTM E96 Procedure B	**0.65**
Water Absorption	%	ASTM D570	**0.15**
Insulation Resistance	$Ohms/cm^2$	ASTM D257	**10^{12}**
Storage Temperature Range	°C		**<30**
Application Temperature Range	°C		**+5°C to +50°C**
Service Temperature Range	°C		**-20°C to +75°C**

TECHNOBIT products are tested at random intervals by independent laboratories to international standards and the results of these tests are available on request. In addition, each batch manufactured is subject to strict quality control procedures to ensure it meets appropriate and applicable standards and/or norms.

- Product Technical specifications may be updated by TechnoBit without prior notice.
- Issue Date of this Techinical Data Sheet is **MAY / 2025**
  The Information Provided by This Issue Cancels Any Previous Issues.

ISO 9001 OHSAS 18001 ISO 14001